

## 2116

## OTTOWALL ELEGANCE

### Breathable waterborne paint for refined finishes



Ottowall Elegance is a breathable acrylic waterborne wall paint for interiors boasting excellent whiteness and characterised by an elegant texture that is silky to the touch. Ottowall Elegance is a solution that combines appealing visual appeal and excellent performances, also thanks to its highly resistant film. It is formulated according to a new approach that makes the product highly breathable in moist conditions and compliant with the certifications and protocols that guarantee the highest home living standards. Ottowall Elegance is A+ and INDOOR AIR COMFORT GOLD certified, is consistent with CAM criteria and is suitable for the BREEAM and LEED protocols.



i/

<b>Revision date</b>	13/04/2026
<b>Main properties</b>	<ul style="list-style-type: none"> <li>• high opacity</li> <li>• excellent whiteness</li> <li>• resistant</li> </ul>
<b>Supports</b>	Gypsum and plasterboard; mineral plasters and skim coats; pre-mixed plasters; painted surfaces; concrete.
<b>Colour</b>	Bianco Base and Base Deep. It can be coloured with the Colormaker tinting system; the number of available bases is indicated in the catalogue and in the Colormaker Lab software.

Technical specifications (data measured at 20°C, with 65% R.H.)	Reference	UoM	Values
Specific weight (pycnometer)		kg/l	1.65 ± 0.04 (of the Bianco Base product)
Water vapour permeability	UNI EN ISO 7783		Class V1 (high permeability)
Resistance to brushing while wet	EN ISO 13300		Class 3
Fire reaction on supports A1 and A2	EN 13501-1		A2-s1, d0
Fire reaction paint only	EN 13501-1		B-s1, d0
Coat-over time		hours	4-8
Dry-hard drying		hours	24-48

### Method of use

. Surface and application conditions	Ambient temperature min +10°C / max +35°C, R.H. <80% Temperature of the support min +10°C / max +35°C, R.H. <10%
. Application method	Roller, brush.
. Thinner	Water
. Dilution	Roller 20-30%, brush 30-40%.
. Mixing	Mix the product with care, adding water gradually until you reach the desired application viscosity.

. Theoretical coverage 12-14 m<sup>2</sup>/l for each coat.

## Certifications

<b>INDOOR AIR COMFORT</b>	Compliant
<b>INDOOR AIR COMFORT GOLD</b>	Class A+
<b>VOC Legislation France</b>	Compliant
<b>CAM Italian Construction</b>	Compliant
<b>ABG/AgBB</b>	Compliant
<b>Belgian legislation</b>	Compliant
<b>Blue Angel (DE-UZ 12-a)</b>	Compliant
<b>EU Ecolabel</b>	Compliant
<b>EU Taxonomy</b>	Compliant

## Application cycle

### PLASTERBOARD AND MASONRY

The support must be well seasoned, dry, dust-free and without impurities of any kind, including loose sand and any traces of release agent. Fill any cracks using Titanstucco. On supports that are already painted, remove old peeling paint with a scraper or brush, or apply a paint stripper if the paint does not come away easily in all points. Also remove any lean tempera. At all events, we suggest applying one coat of Titancril waterborne sealer fixative or, alternatively, one coat of suitably diluted Flatfix pigmented sealer primer. Wait for the fixative to dry completely (12-24 hours) before applying the finish.

### APPLICATION CYCLE

Once the support has been adequately prepared, apply two coats of Ottowall Elegance with a 4-8 h interval in between, depending on the environmental conditions and on the support's absorption. Ottowall Elegance must be applied as explained previously.

## Storage

Protect against frost, store at temperatures between +5°C and 35°C.

## Warnings

Do not apply to structures affected by rising damp. Do not apply to warm walls or walls exposed to direct sunlight, especially during summer. Apply the product at temperatures between +5°C and +35°C. Verify the correctness of the colour before proceeding with the application. On adjacent surfaces only use colours of the same production (batch). Clean the tools soon after use and do not disperse the residues in the environment. Keep out of reach of children. For further information, consult the safety data sheet.

## EU limit value (Dir. 2004/42/EC) - (Italian) Leg. Decree 161/2006

Cat. 1/a: matt paints for interior walls and ceilings (gloss≤25@60°) (WB): 30 g/l (2010). Maximum VOC content < 30 g/l.

## Specification items

Application of 2 coats of Ottowall Elegance, after suitably preparing the surfaces to be treated. Includes materials and application, excludes skimming and/or scaffolding.

This information is the result of our practical experience but is purely indicative. For more detailed information, please contact our technical support service. This data sheet annuls and replaces any previous versions.